

The short-time behavior of a classical ferromagnet with double-exchange interaction

H. A. Fernandes and J. R. Drugowich de Felício

*Departamento de Física e Matemática, Faculdade de Filosofia,
Ciências e Letras de Ribeirão Preto, Universidade de São Paulo,
Avenida Bandeirantes, 3900 - CEP 14040-901, Ribeirão Preto, São Paulo, Brazil*

A. A. Caparica*

Instituto de Física, Universidade Federal de Goiás, 74.001-970, Goiânia (GO) Brazil

We investigate the critical dynamics of a classical ferromagnet on the simple cubic lattice with double-exchange interaction. Estimates for the dynamic critical exponents z and θ are obtained using short-time Monte Carlo simulations. We also estimate the static critical exponents ν and β studying the behavior of the samples at an early time. Our results are in good agreement with available estimates and support the assertion that this model and the classical Heisenberg model belong to the same universality class.

PACS numbers:

I. INTRODUCTION

In the last decade many works have been devoted to the study of the perovskite manganites, $A_{1-x}B_xMnO_3$, where A and B are rare-earth and alkaline-earth ions, respectively, and x is the concentration of B . The perovskite manganites are metal oxides that exhibit some remarkable properties. The most noticeable of them is colossal magnetoresistance (CMR), an extremely large change in the resistivity when a magnetic field is applied in the vicinity of the critical temperature T_c . Usually these materials have been studied on the basis of the double-exchange theory^{1,2,3,4,5} (DE). In one of these works, Anderson e Hasegawa² showed that the transfer element is proportional to $\cos(\theta/2)$, where θ is the angle between the ionic neighbouring spins. This result was recently confirmed for layered manganites⁶. Nevertheless, although this theory has succeeded in explaining qualitatively CMR, some authors have argued that it cannot alone provide a complete description of this phenomenon. They suggest that, in addition to the double exchange, a complete understanding of these materials should include strong electron correlations⁷, a strong electron-phonon interaction⁸, or coexisting phases⁹. One might therefore think that double-exchange alone cannot explain CMR in manganites⁸, but this remains an open question. What we know is that in the study of the manganites the double-exchange theory plays an important role, both in the study of CMR and in explaining the presence of a ferromagnetic state (for $x \approx 0.3$) in doped manganites, furnishing the basis for describing manganites with colossal magnetoresistance.

The mechanism of the double-exchange consists of a strong intrasite exchange between localized ions (core spin S_c^i) and non-localized electrons (E_g orbitals). Based

on this hypothesis Zener¹ succeeded in explaining in 1951 the occurrence of the metal ferromagnetic phase in manganites. Due to a strong intrasite exchange interaction the spin of the electron always aligns parallel to the spin of the ion. When an electron hops from site i to site j its spin must also change from being parallel to S_c^i to being parallel to S_c^j , but with an energy loss proportional to the cosine of half the angle between the core spins².

In Ref. [10], the critical behavior of a classical ferromagnet with double-exchange interaction was studied and estimates for the static critical exponents ν , β and γ , and the critical temperature T_c were derived. These simulations indicate that this model belongs to the universality class of the classical Heisenberg model¹¹.

In this paper, we perform short-time Monte Carlo simulations to explore the critical dynamics of a classical ferromagnet with double-exchange interaction. We evaluate the dynamic exponents z , θ and the static exponents ν and β . Our estimates for static indices are in good agreement with previous results available in the literature^{10,12,13} for the same model. In addition, the result for the dynamic exponent z compare well with previous estimates for the classical Heisenberg model. In summary, present results confirm that both models belong to the same universality class.

The article is organized as follows. In the next Section we define the model. In Section III we give a brief description of short-time Monte Carlo technique and present our results; in Section IV we summarize and conclude.

II. THE MODEL

We use the short-time Monte Carlo simulations to investigate the dynamical critical behavior of a classical spin model with double-exchange interaction. We consider a simple cubic lattice $L \times L \times L$ with periodic boundary conditions. The Hamiltonian for such system is given

*Corresponding author:
caparica@if.ufg.br (A. A. Caparica)

by¹⁰

$$\mathcal{H} = - \sum_{\langle i,j \rangle} J \sqrt{1 + \mathbf{S}_i \cdot \mathbf{S}_j}, \quad (1)$$

where $\langle i,j \rangle$ indicates that the sum runs over all nearest-neighbor pairs of lattice site, J is the ferromagnetic coupling constant and the spin $\mathbf{S}_i = (S_i^x, S_i^y, S_i^z)$ is a three-dimensional vector of unit length.

We used lattice sizes $L = 20, 25, 30, 40$ and 60 and performed short-time simulations at the critical temperature¹⁰

$$T_c = 0.74515,$$

in units of J/k_B , where k_B is the Boltzman's constant.

Our estimates for each exponent were obtained from five independent bins. The dynamic evolution of the spins is local and updated by the Metropolis algorithm. For $20 \geq L \geq 40$ the estimate for the exponent θ was performed using 10000 independent samples, while for the exponents z, ν and β we used 5000 samples. For $L = 60$ all the estimates were performed using 2000 samples. In order to maximize the quality of the linear fitting, each exponent is determined in the time interval $[200, 500]$, except for the exponent z which was measured in the interval $[30, 250]$.

III. SHORT-TIME SCALING RELATIONS AND RESULTS

Following the works of Janssen, Schaub and Schmittmann¹⁴ and Huse¹⁵, the study of the critical properties of statistical systems became in some sense simpler, because they allow to circumvent the well-known problem of the critical slowing down, characteristic of the long-time regime. They discovered using renormalization group techniques and numerical calculations, respectively, that there is universality and scaling behavior even at the early stage of the time evolution of dynamical systems without conserved quantities (model A in the terminology of Halperin *et al*¹⁶).

In this new universal regime, in addition to the familiar set of static critical exponents and the dynamic critical exponent z , a new dynamic critical exponent θ is found. This new critical index, independent of the previously known exponents, characterizes the so-called *critical initial slip*, the anomalous increase of the magnetization when the system is quenched to the critical temperature T_c .

Several works on phase transitions and critical phenomena using this technique have been published¹⁷. The results corroborate the prediction of universality and scaling behavior in the short-time regime and the static critical exponents so obtained are in good agreement with well-known values calculated in the equilibrium. In addition, this approach has permitted obtaining more precise estimates for the dynamic critical exponent z .

The dynamic scaling relation obtained by Janssen *et al* for the k -th moment of the magnetization, extended to systems of finite size¹⁸, is written as

$$M^{(k)}(t, \tau, L, m_0) = b^{-k\beta/\nu} M^{(k)}(b^{-z}t, b^{1/\nu}\tau, b^{-1}L, b^{x_0}m_0), \quad (2)$$

where t is time, b is an arbitrary spatial rescaling factor, $\tau = (T - T_c)/T_c$ is the reduced temperature and L is the linear size of the lattice. The exponents β and ν are the equilibrium critical exponents associated with the order parameter and the correlation length, and z is the dynamic exponent characterizing time correlations in equilibrium. For a large lattice size L and small initial magnetization m_0 at the critical temperature ($\tau = 0$), the magnetization is governed by a new dynamic exponent θ ,

$$M(t) \sim m_0 t^\theta \quad (3)$$

if we choose the scaling factor $b = t^{1/z}$.

In addition, a new critical exponent x_0 , which represents the anomalous dimension of the initial magnetization m_0 , is introduced to describe the dependence of the scaling behavior on the initial conditions. This exponent is related to θ as $x_0 = \theta z + \beta/\nu$. In the following section we evaluate the critical exponents θ, z, ν e β using scaling relations obtained from Eq. (2).

A. The dynamic exponent θ

Usually the dynamic critical exponent θ is calculated using Eq. (3) or through the autocorrelation

$$A(t) \sim t^{\theta - \frac{d}{z}}, \quad (4)$$

where d is the dimension of the system.

In the first case, careful preparation of the initial configurations ($m_0 \ll 1$) is essential, as well as the delicate limit $m_0 \rightarrow 0$. In the autocorrelation case, one must to know in advance the exponent z , which is an order of magnitude greater than θ , so that a small relative error in z induces a large error in θ .

In the present work we find the dynamic critical exponent θ using the time correlation of the magnetization¹⁹

$$C(t) = \langle M(0)M(t) \rangle \sim t^\theta. \quad (5)$$

Here, the averaging is over a set of random initial configurations. The time correlation allows the direct calculation of the dynamic exponent θ , without the need of a careful preparation of the initial state nor of the limiting procedure, the only requirement being that $\langle M_0 \rangle = 0$.

In Fig. 1 we show the time dependence of the time correlation $C(t)$ in double-log scale for the system with $L = 60$. Table I shows our estimates for the critical exponent θ along with $d/z, 1/\nu z$ and $\beta/\nu z$.

These results show that for $L \geq 25$ the finite size effects are less than the statistical errors. Therefore, we conclude that the values for an infinite lattice are within the errorbars of our results for $L = 60$.




FIG. 1: Time evolution of the time correlation of the total magnetization on log scales. Errorbars are smaller than the symbols. Each point represents an average over 5 sets of 2000 samples.

TABLE I: Critical exponents for the double-exchange model.

L	θ	d/z	$1/\nu z$	$\beta/\nu z$
20	0.460(4)	1.499(1)	0.766(6)	0.276(3)
25	0.473(4)	1.515(2)	0.734(5)	0.267(3)
30	0.479(8)	1.521(5)	0.748(7)	0.267(2)
40	0.482(4)	1.525(7)	0.743(5)	0.264(1)
60	0.480(7)	1.519(8)	0.738(7)	0.263(2)

B. The dynamic exponent z

In the short-time regime the dynamic critical exponent z can be evaluated using various methods, such as the autocorrelation²⁰ (Eq. (4), with the previous knowledge of θ), or the second moment $M^{(2)}(t)$ ¹⁷ (when the static exponents β and ν are known). In the present work we estimate the exponent z in two independent ways, using two different techniques. First, we used the time-dependent fourth-order Binder cumulant^{18,21}

$$U_4(t, L) = 1 - \frac{\langle M^4 \rangle}{3\langle M^2 \rangle^2}, \quad (6)$$

with ordered initial configurations ($m_0 = 1$). If $\tau = 0$ this equation depends only on t/L^z , according to scaling laws valid in the beginning of the evolution.

In this case, according to the scaling relation Eq. (2), the cumulants obtained in two different lattices obey the equation

$$U_4(t, L_1) = U_4(b^{-z}t, L_2) \quad (7)$$

with $b = L_1/L_2$. This equation shows that the exponent z is obtained by finding the time re-scaling factor b^{-z} which collapses curves for two lattices of different sizes.

In Fig. 2 we show the Binder cumulant as a function of the time for the lattices $L_1 = 60$ and $L_2 = 40$. The line




FIG. 2: The cumulant $U_4(t, L)$ for $L = 40$ and 60 plotted versus time t with initial states $m_0 = 1$. The line shows the lattice $L = 60$ re-scaled in time. The cumulant for both lattice sizes was obtained from five independent bins. For $L = 40$ we used 5000 samples and for $L = 60$ we used 2000 samples.

shows the collapse of the larger lattice re-scaled in time. Our estimate for z , obtained through the χ^2 test²², for $L_1 = 60$ and $L_2 = 40$ is

$$z = 1.98(3) \quad (8)$$

This result is consistent with that obtained by Peczak and Landau²³ for the classical Heisenberg model. Using equilibrium techniques, these authors found $z = 1.96(7)$. We also estimate the exponent z for other lattice sizes and our results are consistent with the Eq. (8). For $L_1 = 40$ and $L_2 = 25$ we obtained $z = 1.96(2)$, whereas for $L_1 = 60$ and $L_2 = 30$ we obtained $z = 1.96(4)$.

A more precise estimate for the dynamic exponent z can be obtained by combining results from samples submitted to different initial conditions ($m_0 = 1$ and $m_0 = 0$). According to the Ref. [24] the function $F_2(t) = M^{(2)}(t)/(M(t))^2$ behaves as $t^{d/z}$ where d is the dimension of the system. This approach proved to be very efficient in estimating the exponent z , according to results for the Ising model, the three- and four-state Potts models²⁴, the tricritical point of the Blume-Capel model²⁵, the Baxter-Wu model²⁶ and nonequilibrium models like Domany-Kinzel and contact process²⁷. In this technique, for different lattice sizes, the double-log curves of F_2 versus t fall on a single straight line, without any rescaling of time, resulting in more precise estimates for z .

The time evolution of F_2 is shown on log scales in Fig. 3 for $L = 60$. In Table I we show the values of d/z for the five lattice sizes. Taking into account the value of this ratio for the lattice $L = 60$ we obtain

$$z = 1.975(4) \quad (9)$$

Our results for z indicate that besides presenting the same static critical exponents double-exchange and




FIG. 3: Time Evolution of F_2 . The error bars, calculated over 5 sets of 2000 samples, are smaller than the symbols.

Heisenberg models have the same dynamic exponent when submitted to the same updating.

C. The static exponents ν and β

The static exponent ν can be obtained by fixing $b^{-z}t = 1$ in Eq. (2) and differentiating $\ln M(t, \tau)$ with respect to τ in the critical point. Taking into account samples with ordered initial configurations ($m_0 = 1$), we obtain the following power law

$$\partial_\tau \ln M(t, \tau)|_{\tau=0} \sim t^{1/\nu z}. \quad (10)$$

In numerical simulations we approximate the derivative by a finite difference; our results were obtained using finite differences of $T_c \pm \delta$ with $\delta = 0.01$, in units of J/k_B . In Fig. 4 the power law increase of Eq. (10) is plotted in double-log scale for $L = 60$.

From the slope of the curve one can estimate the critical exponent $1/\nu z$ (see Table I).

Using the exponent z obtained from $U_4(t, L)$ and the estimate of $1/\nu z$ for $L = 60$, we obtain the static exponent

$$\nu = 0.68(2). \quad (11)$$

while following the scaling relation $F_2(t)$ the result is

$$\nu = 0.682(8). \quad (12)$$

Finally we can evaluate the static exponent β by the dynamic scaling law for the magnetization

$$M(t) \sim t^{-\beta/\nu z}, \quad (13)$$

obtained from Eq. (2), by considering large systems and setting $b = t^{1/z}$ at the critical temperature $\tau = 0$. In Fig. 5 we show the time evolution of the magnetization in double-log scale for $L = 60$. The estimates of the




FIG. 4: The time evolution of the derivative $\partial_\tau \ln M(t, \tau)|_{\tau=0}$ on log scales in a dynamic process starting from an ordered state ($m_0 = 1$). Error bars are smaller than the symbols. Each point represents an average over 5 sets of 5000 samples.




FIG. 5: The time evolution of the magnetization for initially ordered samples ($m_0 = 1$). The errorbars calculated over 5 sets of 2000 samples, are smaller than the symbols.

exponent $\beta/\nu z$ for the five lattice sizes are shown in Table I.

Using the previous result obtained for $1/\nu z$ (Table I), we find

$$\beta = 0.354(5). \quad (14)$$

Our estimates for the static exponents ν and β are in good agreement with the theoretical results of the Ref. [10] ($\nu = 0.6949(38)$ and $\beta = 0.3535(30)$), Ref. [11] ($\nu = 0.7036(23)$ and $\beta = 0.3616(31)$) and Ref. [28] ($\nu = 0.704(6)$ and $\beta = 0.362(4)$), as well as the experimental results of the Ref. [29] ($\beta = 0.37(4)$) and the Ref. [30] ($\beta = 0.374(6)$).

IV. DISCUSSION AND CONCLUSIONS

In this article we have performed short-time Monte Carlo simulations in order to evaluate the dynamic and static critical exponents of a classical ferromagnet with double-exchange interaction. The exponent θ was estimated using the time correlation of the magnetization. We found the dynamic exponent z through the collapse of the fourth-order time-dependent Binder cumulant and also, alternatively, using the function $F_2(t)$ which combines simulations performed with different initial conditions. Using scaling relations for the magnetization and its derivative with respect to the temperature at T_c , we

have obtained the static exponents ν and β which are in good agreement with the values available in literature. Comparison of our results with those for the classical Heisenberg model corroborate the assertion that the models belong to the same universality class.

ACKNOWLEDGMENTS

The authors are grateful to Departamento de Física e Matemática (DFM) at IFUSP for the use of their computer facilities. This work was supported by the Brazilian agencies CAPES (H.A.F) and FUNAPE-UFMG (A.A.C.).

-
- ¹ C. Zener, Phys. Rev. **82**, 403 (1951).
 - ² P. W. Anderson and H. Hasegawa, Phys. Rev. **100**, 675 (1955).
 - ³ P. G. de Gennes, Phys. Rev. **118**, 141 (1960).
 - ⁴ C. M. Varma, Phys. Rev. B **54** 7328 (1996).
 - ⁵ N. Furukawa, J. Phys. Soc. Jpn. **63**, 3214 (1994).
 - ⁶ Q. A. Li, K. E. Gray, J. F. Mitchell, A. Berger, and R. Osgood, Phys. Rev. B. **61**, 9542 (2000).
 - ⁷ A. Asamitsu, Y. Moritomo, R. Kumai, Y. Tomioka, and Y. Tokura, Phys. Rev. B **54**, 1716 (1996).
 - ⁸ A. J. Millis, P. B. Littlewood, and B. I. Shraiman, Phys. Rev. Lett. **74**, 5144 (1995).
 - ⁹ J. W. Lynn, R. W. Erwin, J. A. Borchers, Q. Huang, A. Santoro, J. L. Peng, and Z. Y. Li, Phys. Rev. Lett. **76**, 4046 (1996).
 - ¹⁰ A. A. Caparica, A. Bunker and D. P. Landau, Phys. Rev. B. **62**, 9458 (2000).
 - ¹¹ K. Chen, A. M. Ferrenberg, and D. P. Landau, Phys. Rev. B **48**, 3249 (1993).
 - ¹² Y. Motome and N. Furukawa, J. Phys. Soc. Jpn. **69**, 3785 (2000).
 - ¹³ Y. Motome and N. Furukawa, J. Phys. Soc. Jpn. **70**, 1487 (2001).
 - ¹⁴ H. K. Janssen, B. Schaub, and B. Z. Schmittmann, Phys. B **73**, 539 (1989).
 - ¹⁵ D. A. Huse, Phys. Rev. B **40**, 304 (1989).
 - ¹⁶ B. I. Halperin, P. C. Hohenberg, and S-K. Ma, Phys. Rev. B **10**, 139 (1974).
 - ¹⁷ B. Zheng, Int. J. Mod. Phys. B **12**, 1419 (1998).
 - ¹⁸ Z. B. Li, L. Schulke and B. Zheng, Phys. Rev. Lett. **74**, 3396 (1995).
 - ¹⁹ T. Tomé and M. J. de Oliveira, Phys. Rev. E. **58**, 4242 (1998); T. Tomé, J. Phys. A: Math. Gen. **36**, 6683 (2003).
 - ²⁰ L. Schulke and B. Zheng, Phys. Lett. A **204**, 295 (1995).
 - ²¹ K. Binder, Z. Phys. A **43**, 119 (1981).
 - ²² W. Press *et al.*, *Numerical Recipes* (Cambridge University Press, London, 1986).
 - ²³ P. Peczak and D. P. Landau, J. Appl. Phys, **67**, 5427 (1990).
 - ²⁴ R. da Silva, N. A. Alves, and J. R. Drugowich de Felício, Phys. Lett. A **298**, 325 (2002).
 - ²⁵ R. da Silva, N. A. Alves, and J. R. Drugowich de Felício, Phys. Rev. E **66**, 026130 (2002).
 - ²⁶ E. Arashiro and J. R. Drugowich de Felício, Phys. Rev. E **67**, 046123 (2003).
 - ²⁷ R. da Silva, R. Dickman, and J. R. Drugowich de Felício, Phys. Rev. E **70**, 067701 (2004).
 - ²⁸ C. Holm and W. Janke, Phys. Rev. B **48**, 936 (1993).
 - ²⁹ K. Ghosh, C. J. Lobb, R. L. Greene, S. G. Karabashev, D. A. Shulyatev, A. A. Arsenov and Y. Mukovskii, Phys. Rev. Lett. **81**, 4740 (1998).
 - ³⁰ M. Sahana, U. K. Rossler, Niloptal Ghosh, Suja Elizabeth, H. L. Bhat, K. Dorr, D. Eckert, M. Wolf, and K. -H. Muller, Phys. Rev. B **68**, 144408 (2003).